

FORMOSA CHEMICALS & FIBRE CORP PLASTICS DIV

201 TUNG HWA N RD, TAIPEI 105 TW

AE8200**Acrylonitrile Butadiene Styrene/Styrene Acrylonitrile, "TAIRILAC", furnished as pellets**

| Color | Min Thk (mm) | Flame Class | HWI | HAI | RTI Elec | RTI Imp | RTI Str |
|-------|-----------------|----------------|-----|-----|-------------|------------|------------|
| ALL | 1.6 | HB | 2 | 0 | 50 | 50 | 50 |
| | 3.0 | HB | 4 | 0 | 50 | 50 | 50 |

Comparative Tracking Index (CTI): **0**

Dimensional Stability (%): -

High-Voltage Arc Tracking Rate (HVTR): **1**High Volt, Low Current Arc Resis (D495): **6**

Dielectric Strength (kV/mm): -

Volume Resistivity (10xohm-cm): -

UL94 small-scale test data does not pertain to building materials, furnishings and related contents. UL94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by ULI.

Report Date: 1997-07-08
Last Revised: 2004-11-30

Underwriters Laboratories Inc®

**IEC and ISO Test Methods**

| Test Name | Test Method | Units | Thickness Tested (mm) | Value |
|--------------------------------|-----------------|---------------|--------------------------|------------|
| IEC Flammability | IEC 60695-11-10 | Class (color) | 1.6 | HB75 (ALL) |
| | | | 3.0 | HB40 (ALL) |
| Glow-Wire Flammability (GWFI) | IEC 60695-2-12 | C | - | - |
| Glow-Wire Ignition (GWIT) | IEC 60695-2-13 | C | - | - |
| IEC Comparative Tracking Index | IEC 60112 | Volts (Max) | - | - |
| IEC Ball Pressure | IEC 60695-10-2 | C | - | - |
| ISO Heat Deflection (1.80 MPa) | ISO 75-2 | C | - | - |
| ISO Tensile Strength | ISO 527-2 | MPa | - | - |
| ISO Flexural Strength | ISO 178 | MPa | - | - |
| ISO Tensile Impact | ISO 8256 | kJ/m2 | - | - |
| ISO Izod Impact | ISO 180 | kJ/m2 | - | - |
| ISO Charpy Impact | ISO 179-2 | kJ/m2 | - | - |

Underwriters Laboratories Inc®