Need more information? Click Here to go to the iQ[™] for Plastics database

Component - Plas	stics						E162823
	IEMICALS & FIBR	E CORP PLAS	STICS DIV				
AG12A3							
Acrylonitrile Bu	itadiene Styrene (AE	3S), "TAIRILAC'	", furnished	as pellets			
	Min Thk	Flame			RTI	RTI	RTI
Color	(mm)	Class	HWI	HAI	Elec	Imp	Str
ALL	1.5-1.65	HB	3	0	60	60	60
Comparati	ive Tracking Index (CTI)	: 0	Dimensional Stability (%): -				
High-Voltage Are	c Tracking Rate (HVTR)	: 2	High Volt, Low Current Arc Resis (D495): 6				
Diel	ectric Strength (kV/mm)): -	Volume Resistivity (10 ^x ohm-cm): -				
	ed solely for determining devices and appliance	the flammability of	plastic materia	Is used in the	components a	nd parts of er	
Report Date: 2007	-02-16						°

Last Revised: 2007-03-27 Underwriters Laboratories Inc®



IEC and ISO Test Methods

		Thickness				
Test Name	Test Method	Units	Tested (mm)	Value		
Flammability	IEC 60695-11-10	Class (color)	1.5-1.65	HB75 (ALL)		
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	С	-			
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	С	-			
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-			
IEC Ball Pressure	IEC 60695-10-2	С	-			
ISO Heat Deflection (1.80 MPa)	ISO 75-2	С	-			
ISO Tensile Strength	ISO 527-2	MPa	-			
ISO Flexural Strength	ISO 178	MPa	-			
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-		
ISO Izod Impact	ISO 180	kJ/m ²	-	-		
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-		

Underwriters Laboratories Inc®

The materials covered in this database are incomplete in certain constructional features or restricted in performance capabilities and are intended for use as components of complete equipment submitted for investigation rather than for direct separate installation in the field. THE FINAL ACCEPTANCE OF THE COMPONENT IS DEPENDENT UPON ITS INSTALLATION AND USE IN COMPLETE PRODUCTS SUBMITTED TO UNDERWRITERS LABORATORIES INC.

Notice of Disclaimer